



CONCREEL HD

THE LEADERS' CHOICE

TEST CERTIFICATE

Portland Slag Cement as per IS 455:2015

REF.: JSW/QA/2023/A-01

DATE : 06-08-2023

WEEK NO. : 27

02-07-2023 08-07-2023


CHARACTERISTIC	RESULTS OBTAINED	REQUIREMENT OF IS 455:2015
(A) CHEMICAL COMPOSITION		
(i) Magnesia (MgO), % by mass	4.79	10.0 Maximum
(ii) Insoluble Residue, % by mass	0.43	4.0 Maximum
(iii) Sulphuric Anhydride (SO ₃) % by mass	2.19	3.5 Maximum
(iv) Sulphide Sulphur (S)	0.20	1.5 Maximum
(v) Loss on Ignition % by mass	0.74	5.0 Maximum
(vi) Total Chloride (Cl), % by mass	0.016	0.10 Maximum
(B) PHYSICAL TESTING		
1. Fineness of Cement		
Sp.Surface (m ² /kg)	346	225 m ² /kg minimum
2. Soundness		
Le-Chatelier Expansion (mm)	1.00	10 mm Maximum
Autoclave Expansion (%)	0.051	0.8 % Maximum
3. Setting Time		
Initial (in Minutes)	215	Not less than 30 minutes
Final (in Minutes)	255	Not more than 600 minutes
4. Compressive Strength (MPa)		
(a) At 72 ± 1 Hr.	29.87	16 MPa Minimum
(b) At 168 ± 2 Hrs.	39.76	22 MPa Minimum
(c) At 672 ± 4 Hrs.	52.87	33 MPa Minimum
5. Normal Consistency	30.75	--
6. GGBS Addition (%)	45.00	25% MIN & 70% MAX

Remarks :

1. Temperature during testing - 27 ± 2° c.
2. Portland Slag Cement conforms to the requirement of IS 455:2015 in all respects.
3. Specific Gravity :- 3.05

Address:

JSW CEMENT LIMITED
 Village- Khar Karavi, Post Office- Gadab
 Taluka- Pen, District- Raigad, PIN-402107
 Maharashtra. +91 2143 277601/2



HOD-Quality Control