



JSW OPC Cement : 53 GRADE

THE LEADERS' CHOICE

TEST CERTIFICATE

Ordinary Portland Cement as per IS 269:2015

REF.: JSW/QA/2023/A-01

DATE : 24-09-2024

WEEK NO. : 34

20-08-2023 26-08-2023

CHARACTERISTIC	RESULTS OBTAINED	REQUIREMENT OF IS 269:2015
(A) CHEMICAL COMPOSITION		
(i) Lime Saturation Factor	0.91	0.80 to 1.02
(ii) Alumina Modulus, Ratio	1.53	0.66 Minimum
(iii) Insoluble residue (IR) % by mass	0.44	5.0 Maximum
(iv) Magnesia (MgO) % by mass	2.54	6.0 Maximum
(v) Sulphuric Anhydride % by mass	2.50	3.5 Maximum
(vi) Loss on ignition (LOI), % by mass	2.57	4.0 Maximum
(vii) Chloride , % by mass	0.016	0.10 Maximum
(B) PHYSICAL TESTING		
1. Fineness of Cement		
Sp.Surface (m ² /kg)	321	225 minimum
2. Soundness		
Le-Chatelier Expansion (mm)	1.00	10 Maximum
Autoclave Expansion (%)	0.053	0.8 Maximum
3. Setting Time		
Initial (in Minutes)	175	30 Minimum
Final (in Minutes)	215	600 Maximum
4. Compressive Strength (MPa)		
(a) At 72 ± 1 Hr.	38.76	27 MPa Minimum
(b) At 168 ± 2 Hrs.	45.87	37 MPa Minimum
(c) At 672 ± 4 Hrs.	55.98	53 MPa Minimum
5. Normal Consistency		
	29.00	--
6. Performance Improver (Slag) %		
	4.00	5 % MAX

Remarks :

1. Temperature during testing - 27 ± 2° c.
2. Ordinary Portland Cement conforms to the requirements of IS 269:2015 in all respects.
3. Specific Gravity :- 3.16

Address:


JSW CEMENT LIMITED
 Village- Khar Karavi, Post Office- Gadab
 Taluka- Pen, District- Raigad, PIN-402107
 Maharashtra. +91 2143 277601/2



Prepared By
Officer-QC



Checked By
SH -QC



Approved By
HOD-QC