



## JSW OPC Cement : 53 GRADE

**THE LEADERS' CHOICE**

### TEST CERTIFICATE

Ordinary Portland Cement as per IS 269:2015

REF.: JSW/QA/2023/A-01

DATE : 01-10-2023

WEEK NO. : 35

27-08-2023 02-09-2023

CHARACTERISTIC	RESULTS OBTAINED	REQUIREMENT OF IS 269:2015
<b>(A) CHEMICAL COMPOSITION</b>		
(i) Lime Saturation Factor	0.90	0.80 to 1.02
(ii) Alumina Modulus, Ratio	1.57	0.66 Minimum
(iii) Insoluble residue (IR) % by mass	0.39	5.0 Maximum
(iv) Magnesia (MgO) % by mass	2.54	6.0 Maximum
(v) Sulphuric Anhydride % by mass	2.22	3.5 Maximum
(vi) Loss on ignition (LOI), % by mass	2.40	4.0 Maximum
(vii) Chloride , % by mass	0.016	0.10 Maximum
<b>(B) PHYSICAL TESTING</b>		
<b>1. Fineness of Cement</b>		
Sp.Surface (m <sup>2</sup> /kg)	337	225 minimum
<b>2. Soundness</b>		
Le-Chatelier Expansion (mm)	1.00	10 Maximum
Autoclave Expansion (%)	0.054	0.8 Maximum
<b>3. Setting Time</b>		
Initial (in Minutes)	175	30 Minimum
Final (in Minutes)	225	600 Maximum
<b>4. Compressive Strength (MPa)</b>		
(a) At 72 ± 1 Hr.	36.84	27 MPa Minimum
(b) At 168 ± 2 Hrs.	45.15	37 MPa Minimum
(c) At 672 ± 4 Hrs.	55.65	53 MPa Minimum
<b>5. Normal Consistency</b>		
	29.00	--
<b>6. Performance Improver (Slag) %</b>		
	4.00	5 % MAX

**Remarks :**

1. Temperature during testing - 27 ± 2° c.
2. Ordinary Portland Cement conforms to the requirements of IS 269:2015 in all respects.
3. Specific Gravity :- 3.16

**Address:**


JSW CEMENT LIMITED  
 Village- Khar Karavi, Post Office- Gadab  
 Taluka- Pen, District- Raigad, PIN-402107  
 Maharashtra. +91 2143 277601/2



Prepared By  
Officer-QC



Checked By  
SH -QC



Approved By  
HOD-QC