



JSW Cement Ltd

P.O. Vidyanagar, Tq : Sandur,  
Dist. Ballari - 583275 Karnataka, India  
Phone : 08395-241001  
Fax : 08395-241003  
Website : www.jsw.in

CIN - U26957MH2006PLC160839



TC-11908



MGMT. SYS.  
RvA C 071



CM/L-6957196

ISO 9001, ISO 14001, ISO 50001 & OHSAS 18001  
Certified by IRQS

## TEST REPORT

		ULR	TC-1190823000000023F
Customer Name & Address:	Marketing JSW CEMENT LTD PO Vidyanagar, Tornagallu, Bellary 583275 , Karnataka	Date Of Issue :	09.10.2023
Let. Ref. No :	NA	Sample Received Date :	09.09.2023
Type of Sample :	PSC	Sample Ref ID :	JSW/VNR/ 787 WEEK No:36
Sample Description :	PORTLAND SLAG CEMENT - CONCREEL HD	Duration of Testing :	10.09.2023 to 08.10.2023
Condition of sample :	UNSEALED	Test Method :	IS: 4032-1985 IS: 4031-1988
Environmental Condition Duration of Testing :	Temperature: 27 °C	Relative Humidity:	65 %

### TEST RESULT CHEMICAL PARAMETERS

Sr. No	Test Parameters	Test Method	Unit	Results	Requirement IS: 455-2015
1	Magnesia Oxide (MgO),(%by mass)	IS: 4032-1985	%	5.50	Maximum 10.0 %
2	Sulphur Trioxide (SO3)(%by mass)	IS: 4032-1985	%	1.70	Maximum 3.5 %
3	Sulphide Sulphur (% by mass)	IS: 4032-1985	%	0.21	Maximum 1.5 %
4	Loss on Ignition (% by mass)	IS: 4032-1985	%	0.86	Maximum 5.0 %
5	Insoluble Residue (% by mass)	IS: 4032-1985	%	0.82	Maximum 4.0 %
6	Chloride Content(%by mass)	IS: 4032-1985	%	0.004	Maximum 0.10 %
7	Alkali Content(%) as Na2O	IS: 4032-1985	%	0.37	Maximum 0.6 %





TC-11908




ISO 9001, ISO 14001, ISO 50001 & OHSAS 18001  
Certified by IRQS

**TEST RESULT**  
**PHYSICAL PARAMETERS**

ULR					TC-1190823000000023F
Sr. No	Test Parameters	Method of tests	Unit	Results	Requirement IS: 455-2015
1	Consistency	IS 4031(Part 4)-1988	%	29.75	Not specified
2	Fineness	IS 4031(Part 2)-1999	M <sup>2</sup> /Kg	346	Shall not be less than 225 m <sup>2</sup> /kg
3	Initial Setting Time	IS 4031(Part 5)-1988	Minutes	160	Shall not be less than 30 Minutes
4	Final Setting Time	IS 4031(Part 5)-1988	Minutes	240	Shall not be more than 600 Minutes
5	Soundness (by Le-Chateliers)	IS 4031(Part 3)-1988	mm	1.00	Shall not be more than 10 mm
6	Soundness (by Autoclave)	IS 4031(Part 3)-1988	%	0.036	Shall not be more than 0.8 %
7	Compressive Strength; a) 72 ± 1h(3 days) b) 168 ± 2h(7 days) c) 672 ± 4h (28 days)	IS 4031(Part 6)-1988	Mpa	20.50 30.70 50.46	Shall not be less than 16.0 Mpa Shall not be less than 22.0 Mpa Shall not be less than 33.0 Mpa

- Note:
- 1) This report is based on the sample received by our laboratory.
  - 2) The test result relates only to the item tested.
  - 3) This report shall not be reproduced, except in full, without the written permission of our Laboratory.
  - 4) Statement of conformity to a specification is provided considering the level of risk associated with decision
  - 5) Measurement Uncertainty is not taken into consideration while stating conformity with the specified requirements as requested by the customer.
  - 6) Any correction invalidates this report.



Reviewed and Authorized by Signature:  
Name: H.K PALIWAL  
Designation: DGM



\*\*\*END OF THE REPORT\*\*\*

Page 02 of 02